

P.T. UNIVERSAL GLOVES

Jalan Pertahanan No.17, Desa Patumbak Kampung, Patumbak-Deli Serdang Prop. Sumut-Indonesia

Tel : (6261) 7883055 Fax : (6261) 7883411

e-mail : marketing@uni-latex.com

PRE-SHIPMENT TESTING REPORT

Reference No. : UG431/VI/14
 Customer : SHANGHAI AMMEX CORPORATION
 Lot No. : CN14157/JL71-0614
 Brand : CHINA GWORKS
 Quantity : 3,286 CARTONS
 Cont Number : TCKU4729305
 Desc of Goods : NITRILE NON-MEDICAL GLOVES POWDER FREE
 Specification : ASTM D6319-10, MIL-STD 105E, ISO 2859-1 /
 SINGLE SAMPLING PLAN FOR NORMAL INSPECTION

XS	S	M	L	XL	Total
-	1,000	1,686	600	-	3,286 cartons

INSPECTION

1. Water-tight Testing and Visual Inspection

Water-tight Test Inspection Level : G-1 - AQL 4.0 Ac 21 - Re 22			Visual Inspection / Major Inspection Level : G-1 - AQL 2.5 Ac 21 - Re 22			Visual Inspection / Minor Inspection Level : G-1 - AQL 4.0 Ac 21 - Re 22		
Size	Sample (pcs)	Defect (pcs)	Size	Sample (pcs)	Defect (pcs)	Size	Sample (pcs)	Defect (pcs)
XS	-	-	XS	-	-	XS	-	-
S	152	3	S	152	3	S	152	4
M	257	5	M	257	4	M	257	6
L	91	1	L	91	2	L	91	2
XL	-	-	XL	-	-	XL	-	-
Total	500	9	Total	500	9	Total	500	12
Result			Result			Result		
OK			OK			OK		

2. Physical Dimension / Inspection Level : S2 - AQL 4.0 / Sample size 13pcs / Ac 1 - Re 2

Size	Length (mm)	Width (mm)	Thickness			Tens. Strength		Elongation		Weight (gram)
			Finger (mm)	Palm (mm)	Cuff (mm)	Before Aging	After Aging	Before Aging	After Aging	
S	242	82	0.05	0.06	0.08	16.83	15.73	580	479	3.2
S	241	83	0.04	0.06	0.08	16.88	15.88	575	483	3.2
S	242	83	0.04	0.06	0.08	16.89	15.79	573	497	3.3
S	240	83	0.04	0.06	0.08	17.04	15.84	579	491	3.2
M	240	94	0.05	0.06	0.08	17.01	15.81	568	480	3.5
M	241	94	0.04	0.06	0.09	16.95	16.15	574	485	3.6
M	241	94	0.04	0.06	0.08	17.03	16.03	582	486	3.6
M	242	92	0.04	0.06	0.09	16.99	15.89	574	475	3.6
M	241	93	0.04	0.06	0.08	16.92	15.72	569	494	3.5
M	241	92	0.04	0.06	0.08	17.05	15.95	565	476	3.5
M	240	93	0.04	0.06	0.08	17.00	15.80	572	487	3.4
L	241	103	0.05	0.06	0.08	17.06	16.06	567	475	3.9
L	240	103	0.05	0.06	0.08	17.01	16.11	568	481	3.8

Length (mm)

Minimum 240 mm

Thickness (mm)

Cuff 0.04 +/- 0.01

Palm 0.06 +/- 0.01

Finger 0.08 +/- 0.01

Tensile Strength

Before Aging 14 Mpa min

After Aging 14 Mpa min

Elongation at Break

Before Aging 500% min

After Aging 400% min

Weight

XS - 3.0

S - 3.2

M - 3.5

L - 3.9

XL - 4.1

Tolerance +/-0.2

3. Packaging Appearance & Conditions

TAPING	CARTON INTEGRITY	WRAP STRAP
OK	OK	OK

Conclusion :

Based on the above findings, we hereby confirm that the goods inspected are good for shipment.

Status : **P A S S**

Stamp & Sign :

P.T. UNIVERSAL GLOVES
SUMUT - INDONESIA