

TEST REPORT



ASIA

RM 1801-02, 1808 & RM 2010,
TOWER B, REGENT CENTRE,
63 WO YI HOP ROAD, KWAI CHUNG,
NEW TERRITORIES, HONG KONG
TEL: (852) 2429 7022, FAX: (852) 2429 7266
ctcasia@ctcgroup.com

Report No.: 00983B-11

This test report supersedes the report 00983-11 issued on March 23, 2011

April 26, 2011

Page 1/3

APPLICANT:
SHANGHAI CHANGXING TEXTILE CO., LTD.

MR. WANG (王根來)
DEPT: SALES (銷售)
NO. 971 ZHAOJIANG ROAD, ZHAOTUN TOWN,
QINGPU DISTRICT, SHANGHAI, 201711, CHINA
上海市青浦区赵屯镇赵江路 971 号

Test(s) requested : CONTRACT HEAT **Product Category :** -- **Product Type :** --

Sample description: HEAT AND CUT RESISTANCE GLOVE, DOUBL-PLY, OUTER IS KEVLAR MATERIAL, COTTON INNER LINING, HEAVEY WEIGHT, KNIT WRIST. COLOR: YELLOW/WHITE (防割耐熱手套)

Style / Article no. : 0202
Ref no. : 0202
Order no. : --

Buyer : --
Exported to : --
Date of receipt of application form : Mar 16, 2011
Date of receipt of sample : Mar 16, 2011
Testing period : March 16, 2011 – March 23, 2011
Service required : REGULAR

Number of sample(s) : 3 PAIRS OF GLOVES

1. Conclusion:

Testing	Result	Combine / Separate Test Item(s)	Failed Test Item(s)
Contact heat	Level 3	(S01)	---

The contact heat got level 3 according to EN 407 standard.

Approved by

John Cheung Fai Cheong
Assistant Laboratory Supervisor

This report is issued by CTC Asia Ltd. under its General Conditions printed overleaf. The results shown in this report refer only to the sample(s) tested. Except by special arrangement, the test items will not be retained by CTC Asia Ltd. for more than 2 months. The test report shall not be reproduced, except in full, without the written approval of the testing laboratory. Hong Kong Accreditation Service (HKAS) has accredited this laboratory under the Hong Kong Laboratory Accreditation Scheme (HOKLAS) for specific laboratory activities as listed in the HOKLAS Directory of Accredited Laboratories. The results shown in this report were determined by this laboratory in accordance with its terms of accreditation.

ASIA

RM 1801-02, 1808 & RM 2010,
TOWER B, REGENT CENTRE,
63 WO YI HOP ROAD, KWAI CHUNG,
NEW TERRITORIES, HONG KONG
TEL: (852) 2429 7022, FAX: (852) 2429 7266
ctcasia@ctcgrupe.com

Report No.: 00983B-11

This test report supersedes the report 00983-11
issued on March 23, 2011

April 26, 2011

Page 2/3

APPLICANT:
SHANGHAI CHANGXING TEXTILE CO., LTD.


2. Label(s) on the sample(s):


Sample(s) (01)	ID	Size	Style/Art. No.	Sub-sample(s) (a)	Component(s) Palm/Palm Back	Colour
(01)	i	--	0202	(a)	Palm/Palm Back	Yellow
(01)	ii	--	0202	(a)	Palm/Palm Back	Yellow
(01)	iii	--	0202	(a)	Palm/Palm Back	Yellow

Remarks: (1) ID is used for identification in which the numbers of sample received are of the same article, ref. no., colour, etc.

3. Sample(s) description assigned by laboratory:

Test item (S01)	Sample(s) (01)-i+ii+iii (a)	Combine / Separate sub-sample(s)
--------------------	-----------------------------------	----------------------------------





TEST REPORT



ASIA

RM 1801-02, 1808 & RM 2010,
TOWER B, REGENT CENTRE,
63 WO YI HOP ROAD, KWAI CHUNG,
NEW TERRITORIES, HONG KONG
TEL: (852) 2429 7022, FAX: (852) 2429 7266
ctcasia@ctcgroup.com

Report No.: 00983B-11

April 26, 2011

This test report supersedes the report 00983-11 issued on March 23, 2011

Page 3/3

APPLICANT:
SHANGHAI CHANGXING TEXTILE CO., LTD.

4. Test Results :

TEST METHOD	Test item(s) (S01)							Requirement	P/F
	100	250	350	500	Melting	Innermost Layer			
1 Contact heat (EN 407:2004 §5.2) Contact temperature (°C) Trial	1	71.3	23.3	17.2	13.8		No	---	
	2	74.1	22.5	17.1	13.9		No	---	
	3	71.0	22.3	17.4	13.9		No	---	
	Mean	72.1	22.7	17.2	13.9		---	---	
Threshold time (t _i) Performance Level :	72	23	17	14	3		---	---	

Performance level in accordance with EN 407 §5.2

Performance level	Contact temperature (°C)	Threshold time (s)
1	100	≥15
2	250	≥15
3	350	≥15
4	500	≥15

Note: P: Pass F: Fail

- End of report -

This report is issued by CTC Asia Ltd. under its General Conditions printed overleaf. The results shown in this report refer only to the sample(s) tested. Except by special arrangement, the test items will not be retained by CTC Asia Ltd. for more than 2 months. The test report shall not be reproduced, except in full, without the written approval of the testing laboratory. Hong Kong Accreditation Service (HKAS) has accredited this laboratory under the Hong Kong Laboratory Accreditation Scheme (HOKLAS) for specific laboratory activities as listed in the HOKLAS Directory of Accredited Laboratories. The results shown in this report were determined by this laboratory in accordance with its terms of accreditation.